SW2015	Ε
(WT)	(D)
(SEE NOTE 7)	

Revision level			Revision Record	Changed	Date	Approved	Date
Drawing	State	Part	TREVISION RECORD	Orlangea	Date	прргочец	Date
01.1	Design Release		SEE ECN# 013944	CAS	7/11/2017	KAC	7/11/2017

	Shrink	Nominal Trade	Suppl	ied	Recovered Diameter (d)		Wall Thickness		Color			
Туре	Ratio	Size	Diamete	er (D)			Recovered (WT)					
	Katio	in	in	mm	in	mm	in	mm				
									Black (BK)			
HIS-Pack-3/64	2:1	3/64	0.047	1 2	0.024	0.6	0.016	0.40	Red (RD)			
1113-Fack-3/04	2.1	3/04	0.047	1.2	0.024	0.6	0.016	0.40	Clear (CL)			
									Blue (BU)			
									Black (BK)			
HIS-Pack-1/16	2:1	1/16	0.063	1.6	0.032	0.8	0.016	0.40	Red (RD)			
1113-1 dck-1/10	2.1	1/10	0.003		0.032			0.40	Clear (CL)			
									Blue (BU)			
									Black (BK)			
HIS-Pack-3/32	2:1	3/32	0.094	2.4	0.047	1.2	0.02	0.5	Red (RD)			
1113 1 dek 3/32		3,32	0.054		0.047	1.2	0.02	0.5	Clear (CL)			
									Blue (BU)			
									Black (BK)			
									Red (RD)			
HIS-Pack-1/8	2:1	1/8	0.125	3.2	0.063	1.6	0.02	0.5	Clear (CL)			
									Blue (BU)			
									Green-Yellow (GNYE)			
									Black (BK)			
									Red (RD)			
HIS-Pack-3/16	2:1	3/16	0.188	4.8	0.094	2.4	0.02	0.5	Clear (CL)			
									Blue (BU)			
									Green-Yellow (GNYE)			
			0.25	6.4	0.125	3.2	0.024	0.6	Black (BK)			
	2:1								Red (RD)			
HIS-Pack-1/4		1/4							Clear (CL)			
									Blue (BU)			
									Green-Yellow (GNYE) Black (BK)			
					0.185	4.7	0.024	0.6	Red (RD)			
LIC Dack 2/9	2:1	3/8	0.275	0.5					Clear (CL)			
HIS-Pack-3/8	2.1	3/0	0.375	9.5					Blue (BU)			
									Green-Yellow (GNYE)			
												Black (BK)
	/2 2:1			12.7	0.25				Red (RD)			
HIS-Pack-1/2		1/2	0.5			6.4	0.024	0.6	Clear (CL)			
1113-F dCK-1/2									Blue (BU)			
									Green-Yellow (GNYE)			
									Black (BK)			
									Red (RD)			
HIS-Pack-3/4	2:1	·	0.75	25.4	0.38	9.5		0.8	Clear (CL)			
1113 1 461 57 1					0.50				Blue (BU)			
									Green-Yellow (GNYE)			
					0.5	12.7			Black (BK)			
								0.9	Red (RD)			
HIS-Pack-1									Clear (CL)			
									Blue (BU)			
									Green-Yellow (GNYE)			
	1											

NOTES:

- 1. SHRINK RATIO: 2:1
- 2. LONGITUNDINAL CHANGE AFTER SHRINKAGE: -5%MAX
- 3. MINIMUM SHRINK TEMPERATURE: 248° F (120° C)
- 4. OPERATING TEMPERATURES: -67° F TO 275° F (-55° C TO +135° C)
- 5. DIELECTRIC STRENGTH: 25kV/MM ACCORDING TO IEC 60684 P2
- 6. FLAMMABILITY: ASTM D2671
- 7. CONSULT FACTORY OR WEBSITE FOR AVAILABLE LENGTHS

Material
POLYOLEFIN, CROSS LINKED (POX)

Units:	inches
	nsion without nces details to:
.XXX	$X = \pm .0005$
.XX	$X = \pm .005$
.X	$X = \pm .01$

 $.X = \pm .03$

None = $\pm .06$

 \angle = ±0.5°

Dimension Formatted in/[mm]

The copyright of this drawing is reserved by HellermannTyton. It is issued on condition that it is not reproduced, copied, or disclosed to a third party, either wholly or in part, without the consent of HellermannTyton.

Approved	KAC	12/9/2016
Drawn	GRW	12/9/2016

North America Email: corp@htamericas.com Web: www.hellermann.tyton.com

	Article/Type-No HIS-PACK SERIES	Scale	5:1
	HEAT SHRINK TUBING, 2:1 SHRINK RATIO,	Project Nu	mber
)	NON-ADHESIVE THIN WALL	PRP 1	7-10

Drawing-No PRODUCTION : Phas 17-1046-001-CSU

	PRP	17-1046
ise	Format	A 1 1

ΑН Sheet 1/1